



# Specification Sheet

## Z-Select 4000T All-Temp

### Features:

- Thermal transfer, premium, ultra smooth, paper label with an all-temp permanent acrylic adhesive
- Excellent high speed print quality
- Adhesive allows application down to -20° F (-29° C)
- Topcoating is suitable for fanfolding
- Meets FDA 175.105 for indirect food contact requirements
- Available in white (05273RM)

### Suggested Applications:

- Labeling of packaging material including corrugate, plastic, glass, and metal
- Frozen food labeling
- Compliance labeling
- Labeling of laboratory specimen containers
- Work in process labeling

### Material Construction:

	Description	Caliper
Facestock	White smooth topcoated paper	3.2 mil
Adhesive	High performance, acrylic-based	0.8 mil
Liner	40 lb. semi-bleached, kraft stock	2.5 mil
	<b>Total</b>	<b>6.5 mil</b>

### Temperature Performance:

- Minimum Application Temperature: -20° F (-28° C)
- Service Temperature: -65° F to 200° F (-54° C to 93° C)
- Storage Conditions: 32° F to 70° F (0° C to 21° C) at 35% to 50% RH
- Expected Exterior Life: Not recommended for outdoor use





# Specification Sheet

## Z-Select 4000T All-Temp

### Suggested Ribbons for Applications with Chemicals

Ribbon	Weak					Moderate				Harsh			Extreme				
	Blood	Body Fluid	Salt Water	Water	Window Cleaner	Alcohol	Ammonia	Bleach	IPA	Gasoline	Grease	Oil	Acetone	IR Reflow	MEK	TCE	Xylene
2000			X	X	X												
2100			X	X	X												
5319			X	X	X												
3200			X	X	X												

### 180° Peel Room Temperature Peel Adhesion (oz/in):

Corrugate		Steel		Polycarbonate		Polyethylene	
5 min	24 hr	5 min	24 hr	5 min	24 hr	5 min	24 hr
14	21	*	*	31	59	26	37

\*Attraction between adhesive and surface is so great that the facestock rips.

NOTE: For guidance only, not to be used for setting specifications

### Product Performance and Suitability

The information contained in this document is to be used for guidance only and is not intended for use in setting specifications. All purchasers of Zebra products shall be solely responsible for independently determining if the product conforms to all requirements of their unique application.

